

TECHNICAL DATA SHEET

kelteks NEEDLED REINFORCEMENT
CNL-1035-345/345/345-WR/WR/WR

Specifications		Unit	Value	Tolerance	Standard
Fiber material	E/ECR-Glass	-	-	-	-
Raw material Warp	Direct Roving	tex	300	-	-
Raw material Weft	Direct Roving	tex	300	-	-
Input Material Layer 1	Woven Roving	g/m ²	345	-	ISO 3374
Input Material Layer 2	Woven Roving	g/m ²	345	-	ISO 3374
Input Material Layer 3	Woven Roving	g/m ²	345	-	ISO 3374
Connection of layers	Needled	-	-	-	-
Shape	Roll	-	-	-	-
Basis weight	-	g/m ²	1.035	± 8%	ISO 3374
Width	-	cm	125	+1 / -3	ISO 22198
Length	-	m	95	-	ISO 22198
Density	Warp	threads/10cm	55	± 1	ISO 4602
	Weft	threads/10cm	60	± 1	ISO 4602
Weave	Plain	-	-	-	ISO 2113
Cardboard diameter	-	mm	150	-	-

Information

1. This product is still in development stage and the values given in this TDS are on the basis of preliminary results for information only and might change.

2. Disclaimer

2.1. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any liability arising out of its use or performance. The user, by accepting the products described herein, agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Kindly note that under certain conditions the properties can be affected to a considerable extent by the machining or processing. Application, use, and processing of products is effected beyond our possible control, and accordingly is the sole and exclusive responsibility of recipients. Statements in this data sheet shall not be construed as representations of warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation.

R&D DATA